

Application No.: 10/674999

Case No.: 58227US002

Amendments to the Claims:**BEST AVAILABLE COPY**

Please cancel claims 32-41, 43-45 and 56-59 without prejudice or disclaimer. Please amend claims 18, 21 and 25 to appear as in the Listing of Claims.

The following Listing of Claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims

1. (Previously presented) A composition for forming an insulating layer, the composition comprising:
a mixture comprising surface modified inorganic nanoparticles present in an amount of 5 to 95 percent by weight of the mixture dispersed in polymethylsilsesquioxane present in an amount of 5 to 95 percent by weight of the mixture, wherein the surface modifier comprises a carboxylic acid, a carboxylic acid derivative, a silane, or mixtures thereof;
a solvent; and
one or more optional additives,
wherein the composition has a viscosity suitable for applying the composition using a digital printing technique.
2. (Original) The composition of claim 1, wherein the composition has a viscosity of 1 to 100,000 centipoise measured using continuous stress sweep, over shear rates of 1 s^{-1} to 1000 s^{-1} .
3. (Original) The composition of claim 1, wherein the composition has a viscosity suitable for ink jet printing.
4. (Original) The composition of claim 3, wherein the composition has a viscosity of 1 to 40 centipoise measured using continuous stress sweep, over shear rates of 1 s^{-1} to 1000 s^{-1} .
5. (Original) The composition of claim 1, wherein the nanoparticles comprise one or more of silica, zirconia, and alumina particles.

Application No.: 10/674999

Case No.: 58227US002

BEST AVAILABLE COPY

6. (Cancelled).
7. (Cancelled).
8. (Previously presented) The composition of claim 1, wherein the carboxylic acid derivatives comprise hexanoic acid or 2[-2-(2-methoxyethoxy)ethoxy] acetic acid.
9. (Previously presented) The composition of claim 1, wherein the silanes comprise methyltriethoxysilane, methyltrimethoxysilane, isobutyltriethoxysilane, isobutyltrimethoxysilane, isooctyltriethoxysilane, isooctyltrimethoxysilane, or mixtures thereof.
10. (Original) The composition of claim 1, wherein the nanoparticles have an average size of 1 to 500 nanometers.
11. (Original) The composition of claim 1, wherein the nanoparticles have an average size of 5 to 125 nanometers.
12. (Original) The composition of claim 1, wherein the one or more optional additives are present in an amount of 0 to 60 percent by weight of the composition after evaporation of substantially all the solvent.
13. (Original) The composition of claim 1, wherein the one or more optional additives comprise an adhesion promoter.
14. (Original) The composition of claim 13, wherein the adhesion promoter comprises polyethyloxazoline.

BEST AVAILABLE COPY

Application No.: 10/674999

Case No.: 58227US002

15. (Original) The composition of claim 13, wherein the adhesion promoter is present in an amount of 0 to 5 percent by weight of the composition after evaporation of substantially all the solvent.

16. (Previously presented) A composition for forming an insulating layer, the composition comprising:

a mixture comprising surface modified inorganic nanoparticles present in an amount of 5 to 95 percent by weight of the mixture dispersed in polymethylsilsesquioxane present in an amount of 5 to 95 percent by weight of the mixture;

a solvent; and

an additive comprising one or more tetraalkoxysilanes and alkyltrialkoxysilanes,

wherein the composition has a viscosity suitable for applying the composition using a digital printing technique.

17. (Original) The composition of claim 16, wherein the alkoxysilanes are selected from the group consisting essentially of tetraethoxysilane, tetramethoxysilane, methytriethoxysilane, and methyltrimethoxysilane.

18. (Currently amended) The composition of claim 16, wherein the one or more tetraalkoxysilanes and alkyltrialkoxysilanes are present in an amount of ~~0 to~~ 50 percent or less by weight of the composition after evaporation of substantially all the solvent.

19. (Original) The composition of claim 1, wherein the one or more optional additives comprise a flexibilizer.

20. (Previously presented) A composition for forming an insulating layer, the composition comprising:

a mixture comprising surface modified inorganic nanoparticles present in an amount of 5 to 95 percent by weight of the mixture dispersed in polymethylsilsesquioxane present in an amount of 5 to 95 percent by weight of the mixture;

Application No.: 10/674999

Case No.: 58227US002

a solvent; and
an additive comprising a flexibilizer comprising one or more of dialkyldialkoxysilanes and trialkylmonoalkoxysilanes,
wherein the composition has a viscosity suitable for applying the composition using a digital printing technique.

21. (Currently amended) The composition of claim 20, wherein the one or more dialkyldialkoxysilanes and trialkylmonoalkoxysilanes are selected from the group consisting ~~essentially~~ of dimethyldiethoxysilane, dimethyldimethoxysilane, trimethylethoxysilane, and trimethylmethoxysilane.

22. (Original) The composition of claim 19, wherein the flexibilizer is present in an amount of 0 to 40 percent by weight of the composition after evaporation of substantially all the solvent.

23. (Previously presented) A composition for forming an insulating layer, the composition comprising:

a mixture comprising surface modified inorganic nanoparticles present in an amount of 5 to 95 percent by weight of the mixture dispersed in polymethylsilsesquioxane present in an amount of 5 to 95 percent by weight of the mixture;

a solvent; and

an additive comprising an organic acid,

wherein the composition has a viscosity suitable for applying the composition using a digital printing technique.

24. (Original) The composition of claim 23, wherein the organic acid comprises acetic acid, methoxyethoxyacetic acid, hexanoic acid, or mixtures thereof.

25. (Currently amended) The composition of claim 23, wherein the organic acid is present in an amount of ~~0 to~~ 3 percent or less by weight of the composition after evaporation of substantially all the solvent.

BEST AVAILABLE COPY

Application No.: 10/674999

Case No.: 58227US002

26. (Original) The composition of claim 1, wherein the solvent comprises an alcohol, a ketone, an ether, an acetate, or mixtures thereof.

27.-59. (Cancelled).